




559

UL 181A-P & B-FX Cold weather Foil Tape



- Backing:** Printed Aluminum Foil
- Adhesive:** Acrylic Adhesive
- Liner:** Natural Kraft Paper
- Colors:** Aluminum
- Specifications:** UL 181 A-P & UL 181B-FX Listed
- Standard Sizes:** 2.5in x 60yd, 72mm x 55M

Applications

- Permanently seals seams in fiberglass duct board and flexible ducts for HVAC systems
- Durable seal for dryer ventilation
- Suitable for sealing metal to metal seams on rigid sheet metal ducts

Features

Benefits

- | | |
|--|---|
| <ul style="list-style-type: none"> • Aggressive Cold Weather Acrylic Adhesive • Natural Kraft Release Liner • UL 181A-P & 181B-FX Listed • Low VOC Content | <ul style="list-style-type: none"> • Superior performance in all climate conditions • Resists mold & mildew growth • Reduced environmental impact • Meets code requirements and can contribute toward requirements for EA Credit 1 (Optimize Energy Performance) under LEED® • Can contribute toward satisfying EQ Credit 4.1 (Low Emitting Materials) under LEED® |
|--|---|

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Total Thickness	4.8 mils	0.122 mm	ASTM D-1000
Foil Thickness	2.1 mils	0.053 mm	ASTM D-1000
Adhesion to Steel	68 oz/in	7.44 N/cm	PSTC-101
Adhesion to Backing	60 oz/in	6.56 N/cm	PSTC-101
Tensile Strength	27 lb/in	47.28 N/cm	ASTM D-1000
Operating Temperature	-20 to 325 °F	-29 to 163 °C	
Application Temperature	-10 to 200 °F	4 to 93 °C	
Flame Spread	3		
Smoke Developed	0		
VOC Content	<30 g/L		

Recommended Storage Conditions: 60-80 °F at 40-60% RH
 Standard Shelf Life (at 25 °C): 36 months from date of manufacture.

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To Berry's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are typical values submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.