



A.B. MASTIC 33-01

COLOR

Black

SERVICE TEMPERATURE

0 to 200°F
(-17.8 to 93°C)

WATER VAPOR TRANSMISSION

Breather-Type coating.

COVERAGE

.125" wet film equals 12.8 sq. ft./gal. The coverage rate is dependent on the surface being covered and the application method.

WEIGHT PER GALLON

9 lb.

AVERAGE NONVOLATILE

45% by weight

DRYING TIME

Touch: 1 hr.

Through: 12 hr.

The drying time depends on the temperature, humidity and film thickness.

SAFETY

Flammability

Wet: Nonflammable

Dry: Slow burning

DESCRIPTION

33-01 A.B. Mastic is an asphalt emulsion breather type mastic. It is designed to provide weather protection to hot insulation installations. It is easily applied by trowel or glove over a reinforcing membrane of wire, metal lath or glass cloth.

LIMITATIONS

Keep from freezing.

Apply between 40°F (4.4°C) and 110°F (43°C)

Do not apply to plastic foam insulation outdoors.

METHOD OF APPLICATION

Trowel

MATERIAL PREPARATION

Do not thin.

APPLICATION

This product is for industrial use only. It should be applied by trained and qualified craftspeople. Prime dusty surfaces. Be sure surfaces are clean and dry. Use firm even trowel strokes to work 33-01 into the reinforcing membrane. Smooth with trowel to finish.

CLEANUP

Water or mineral spirits.

CAUTION:

Avoid prolonged or repeated contact with skin. Do not take internally. In an emergency, call a physician. Keep out of reach of children.

ASBESTOS FREE

Warranty Terms: The physical and chemical properties of this product are representative of the typical average values derived in accordance with test methods deemed acceptable, and can vary when subjected to normal manufacturing methods. These values are supplied only as a technical service and are subject to change without notice. To be sure information is current call Mon-Eco Industries, Inc.

Terms of Warranty: Warrantor, Mon-Eco Industries, Inc. warrants satisfactory results of this product only when recommendations herein established are followed. The recommendations for use are established upon tests and information deemed reliable. We recommend that adequate testing be made by the user to determine if the product is suitable for the intended purpose and use. Warrantor assumes no responsibility beyond replacement or refund of the purchase price of this product, since warrantor has no control over the methods and application of its product, methods and conditions of transportation, handling and storage of the product. WARRANTOR EXPLICITLY DISCLAIMS ALL LIABILITY FOR INCIDENTAL OR CONSEQUENTIAL DAMAGE. No agent or representative of Mon-Eco Industries, Inc. has the authority to change or extend these conditions.

Mon-Eco Industries, Inc.

5 Joanna Court • 800-899-6326 • East Brunswick, NJ 08816 732 257-7942 Fax: 732-257-6525